



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1809

Typical Characteristics

Refractive Index Liquid **Series A**
Refractive Index **1.54400** at 589.3 nm and 25 ° C

Composition Aliphatic / Alicyclic Hydrocarbons and Hydrogenated Terphenyl
Appearance Colorless to light yellow liquid
Odor Slight
Color Stability In Direct Sun: may slightly darken after 1 day, more after 4 months, dark after 6 years
Index Change Rate Low : -0.00002 to +0.00005
by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 °C

Index at 20°C 1.54607
Pour Point < -7 °C
Boiling Point > 262 °C (760 mm Hg)
Flash Point > 138 °C (COC)
Brix Value (Per ICUMSA) 99.9 at 20°C
Density 0.962 g / cc at 25 °C
Density Temp Coef -0.0007 g / cc / °C
Coef of Thermal Expansion 0.0007 cc / cc / °C
Thermal Conductivity n/a cal / sec / cm² / °C - 1 cm thickness

Viscosity 57 cSt at 25 °C 55 cP at 25 °C
Surface Tension 34 dynes/cm at 25 °C

Soluble Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene

Partly Soluble Acetone, Ethanol

Insoluble Water

Compatible 10 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Silicone (Sylgard 184) and Fluorosilicone (730 RTV) Rubbers, Tygon F-4040-A, Tygothane; Aluminum, Brass, Copper, Steel

Incompatible Polystyrene, Latex, Neoprene, Silicone (3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series A**
 Refractive Index **1.54400** at 589.3 nm and 25 °C

Cauchy Coefficients
 A: 1.522312E+00
 B: 6.8364E+03
 C: 2.4147626E+08

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	-	-	-	-	-
240.0	-	-	-	-	-
250.0	-	-	-	-	-
270.0	-	-	-	-	-
290.0	-	-	-	-	-
308.0	-	-	-	-	-
355.0	1.592	78	9	0	0
365.0	1.587	97	72	4	0
406.0	1.5727	99	93	47	0
473.0	1.5577	100	99	91	41
532.0	1.5495	100	100	97	73
589.3	1.5440	100	100	98	85
632.8	1.5409	100	100	99	92
656.3	1.5395	100	100	100	95
790.0	1.5339	100	100	100	98
828.0	1.5328	100	100	100	98
981.0	1.530	100	100	97	72
1310.0	1.526	100	99	90	34
1550.0	1.525	100	98	84	17
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0161

Abbe v_D 33.8

Temp. Coefficient -0.000414 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening