



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1809

Typical Characteristics

Refractive Index Liquid **Series A**
Refractive Index **1.54800** at 589.3 nm and 25 ° C

Composition Aliphatic / Alicyclic Hydrocarbons and Hydrogenated Terphenyl
Appearance Colorless to light yellow liquid
Odor Slight
Color Stability In Direct Sun: may slightly darken after 1 day, more after 4 months, dark after 6 years
Index Change Rate Low : -0.00002 to +0.00005
by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 °C

Index at 20°C 1.55007
Pour Point < -7 °C
Boiling Point > 262 °C (760 mm Hg)
Flash Point > 138 °C (COC)
Brix Value (Per ICUMSA) >100 at 20°C
Density 0.969 g / cc at 25 °C
Density Temp Coef -0.0007 g / cc / °C
Coef of Thermal Expansion 0.0007 cc / cc / °C
Thermal Conductivity n/a cal / sec / cm² / °C - 1 cm thickness

Viscosity 60 cSt at 25 °C 58 cP at 25 °C
Surface Tension 34 dynes/cm at 25 °C

Soluble Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene

Partly Soluble Acetone, Ethanol

Insoluble Water

Compatible 10 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Silicone (Sylgard 184) and Fluorosilicone (730 RTV) Rubbers, Tygon F-4040-A, Tygothane; Aluminum, Brass, Copper, Steel

Incompatible Polystyrene, Latex, Neoprene, Silicone (3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series A**
 Refractive Index **1.54800** at 589.3 nm and 25 °C

Cauchy Coefficients
 A 1.525854E+00 B 6.9680E+03 C 2.5099242E+08

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	-	-	-	-	-
240.0	-	-	-	-	-
250.0	-	-	-	-	-
270.0	-	-	-	-	-
290.0	-	-	-	-	-
308.0	-	-	-	-	-
355.0	1.597	78	8	0	0
365.0	1.592	97	71	3	0
406.0	1.5774	99	92	45	0
473.0	1.5620	100	99	91	39
532.0	1.5536	100	100	97	72
589.3	1.5480	100	100	98	84
632.8	1.5448	100	100	99	91
656.3	1.5434	100	100	100	95
790.0	1.5377	100	100	100	98
828.0	1.5366	100	100	100	98
981.0	1.533	100	100	97	73
1310.0	1.530	100	99	90	35
1550.0	1.529	100	98	84	18
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0165

Abbe v_D 33.3

Temp. Coefficient -0.000415 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening