



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1809

Typical Characteristics

Refractive Index Liquid **Series A**
Refractive Index **1.57400** at 589.3 nm and 25 ° C

Composition Hydrogenated Terphenyl and 1-Bromonaphthalene
Appearance Light Yellow Liquid
Odor Slight: unpleasant
Color Stability In Direct Sun: may slightly darken after 1 day, very dark after 4 months, dark with precipitate after 6 yrs
Index Change Rate Low : -0.00003 to +0.00003
by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 °C

Index at 20°C 1.57612
Pour Point < 6 °C
Boiling Point > 279 °C (760 mm Hg)
Flash Point > 113 °C (COC)
Brix Value (Per ICUMSA) >100 at 20°C
Density 1.016 g / cc at 25 °C
Density Temp Coef -0.0007 g / cc / °C
Coef of Thermal Expansion 0.0007 cc / cc / °C
Thermal Conductivity n/a cal / sec / cm² / °C - 1 cm thickness

Viscosity 79 cSt at 25 °C 80 cP at 25 °C
Surface Tension 37 dynes/cm at 25 °C

Soluble Acetone, Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene

Partly Soluble Ethanol

Insoluble Water

Compatible 9 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polyester, Polyethylene, Polypropylene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Silicone (Sylgard 184, 3140 RTV) and Fluorosilicone (Siliastic 730 RTV) Rubbers ; Tygothane, Aluminum, Steel

Incompatible Polycarbonate, Polystyrene, Latex, Neoprene, Tygon (all types except Tygothane), (Acrylic at 55 °C), may tarnish Brass and Copper.



Refractive Index Liquid **Series A**
 Refractive Index **1.57400** at 589.3 nm and 25 °C

Cauchy Coefficients
 A 1.548783E+00 B 7.8302E+03 C 3.2191382E+08

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	-	-	-	-	-
240.0	-	-	-	-	-
250.0	-	-	-	-	-
270.0	-	-	-	-	-
290.0	-	-	-	-	-
308.0	-	-	-	-	-
355.0	-	-	-	-	-
365.0	1.626	96	65	1	0
406.0	1.6081	99	91	37	0
473.0	1.5902	100	99	89	31
532.0	1.5805	100	100	96	67
589.3	1.5740	100	100	98	82
632.8	1.5703	100	100	99	90
656.3	1.5687	100	100	99	95
790.0	1.5622	100	100	100	98
828.0	1.5609	100	100	100	99
981.0	1.557	100	100	98	78
1310.0	1.553	100	99	91	37
1550.0	1.552	100	98	85	20
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0190

Abbe v_D 30.2

Temp. Coefficient -0.000423 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening